TRANSLATION FROM POLISH LANGUAGE

Report from tests No 3/BU/00

RESULTS of TESTS

Note: the results of the tests are the integral part of the report from tests No 3/BU/00 which cannot be used in fragments without a permission from the Institute of Naphta **Technology**

Name of a sample supplied by the customer: Petromix

The results:

	Subject of	Unit	Heavy residual	Heavy residual	Base light	Base light	Method of testing
	tests		fuel oil No"3"	fuel oil No "3"	fuel oil	fuel oil	
				+		+	acc. to
				Petromix		Petromix	
				in ratio:		In ratio:	
				1:10000		1:10000	
1.	Kinematic viscosity at 80°C	mm²/s	94.00+/-0,35	92.66+/-0,35	-	-	PN-81/C-0401
2.	Corrosion on steel pins	corossion degree	after 1 h – no corossion after 6 h – no corossion after 24 h – heavy corossion of "D" degree	after 1 h – no corossion after 6 h – no corossion after 24 h – heavy corossion of "C" degree	-	-	ASTM D 665A Estimation acc to NACE TM 02-75
3.	Interfacial tension water-oil	mN/m	-	-	29.25+/-2%	10.6+/-2%	PN-90/C-04809

a) heavy fuel oil ,,3" acc to PN-76/C-96024

b) base light fuel oil acc to PN-C-96024

Date of tests beginning: 09.05.2000 Date of tests termination: 31.05.2000

Additional pieces of information:

The report was performed on:

31.05.2000

Origin: EU

Distributor: "ORMET", ul. Sadowa 12; 43-100 Tychy; Poland

Tel/fax: +48-32-3230564; www.ormet.com.pl; e-mail: ormetbw@gmail.com